

- b) from 0 to 100 parts by weight of a polyamine-polyamide copolymer prepared from the following monomers:
- α) from 0.5 to 25% by weight, based on the polyamine-polyamide copolymer, of a polyamine having at least 4 nitrogen atoms and having a number-average molecular weight M_n of at least 146 g/mol, and
 - β) a polyamide-forming monomer selected from the group consisting of a lactam, a ω -aminocarboxylic acid, an equimolar combination of a diamine and a dicarboxylic acid and a mixture thereof; and
 - c) from 0 to 80 parts by weight of a polyamide selected from the group consisting of PA11, PA12, PA612, PA1012, PA1212 and a mixture thereof;
- wherein a total of the parts by weight of components a), b) and c) is 100;
- wherein at least 20 parts by weight of components a) and b) is a monomer unit which is obtained from caprolactam and/or from a combination of hexamethylenediamine/adipic acid; and
- wherein at least 20 parts by weight of components b) and c) is a monomer unit which is obtained from ω -aminoundecanoic acid, laurolactam, a mixture of hexamethylenediamine and 1,12-dodecanedioic acid, a mixture of 1,10-decanediamine and 1,12-dodecanedioic acid, and/or a mixture of 1,12-dodecanediamine and 1,12-dodecanedioic acid;
- wherein the molding composition of layer I is obtained by subjecting a blend comprising polyamide a) and polyamide b) to solid-phase post-condensation.

BASIS FOR THE AMENDMENT

The specification and Claim 32 have been amended to recite proper language and to correct minor typographical errors.